# PRO<sup>®</sup> Flash 14



Self-adhesive Window & Door Flashing Tape

# **Technical Data Sheet**

**Pro®** Flash 14 is a self-adhering membrane **PP** film with butyl hybrid adhesive on a PET liner.

### Features & Benefits:

High strength PP film and adhesive which seals around nails and prevents water intrusion Installation temperature range 10°F to 150°F Butyl hybrid adhesive with excellent low and high temperature flexibility and adhesion Puncture resistant UV resistant

### **Technical Data:**

- $\Rightarrow$  Adhesive: Butyl Hybrid
- $\Rightarrow$  Backing PP Film
- $\Rightarrow$  Liner: PET liner
- $\Rightarrow$  Thickness without liner: 14 mils (ASTM D1777)
- $\Rightarrow$  Adhesion to Stainless Steel: 160 oz./in (PSTC-1)
- $\Rightarrow$  Elongation: > 600% (ASTM D882)
- $\Rightarrow$  Water Resistance: > 24 Hours (Class A) (ASTM D779)
- ⇒ Puncture Resistance Dart Drop: 500 g (ASTM D1709 Meth A)
- $\Rightarrow$  Penetration Resistance: 4.5 lbf (ASTM F1306)
- ⇒ WVTR: < 0.1 perms (ASTM E96 (Desiccant)
- $\Rightarrow$  Application Temperature: 10°F to 150°F
- $\Rightarrow$  Service Temperature: -30°F to 200°F
- $\Rightarrow$  Colors Available: White & Black

#### **Application:**

Pro® Flash 14 common applications include sealing around windows, doors, and other openings and transitions in exterior walls.



621 Route One South. North Brunswick, NJ 08902 Toll Free #1-800-345-0234 sales@protapes.com

Note: The above are typical values and should not be used in writing specifications. The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representatives, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications. Tape should be stored in its original packaging in a cool dry area away from direct sunlight and should be used within 12 months from date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminates. Adhesives are compliant with FDA regulations for indirect food contact—CFR 175.105